



RoHS
2002/95/EC

ScotchcastTM

Electrical Insulating Resin 4

Data Sheet

April 2008

Product Description

3MTM Scotchcast Electrical Insulating Resin 4 is a two-part, epoxy insulating and encapsulating resin. This resin, mixed in its unique two-part bag, generates its own heat to cure. Its compatibility with solid and synthetic cable insulations and jackets makes Resin 4 an excellent insulator and sealer for cable splicing. Use Resin 4 to splice solid dielectric and oil filled cables up to 8 kV and to jacket high-voltage splices through 69 kV. It is used in 3M Splice Kit Series 82 and 90-B1.

Scotchcast Resin 4 is packaged in the following sizes:

Size	g	cc	oz	cu in.
A	88	78	3.1	4.8
B	205	181	7.2	11.1
C	414	366	14.6	22.5
D	619	548	21.8	33.6
D-NZ	872	772	30.8	47.3
E	288	255	10.2	15.6

Resin Features

- Excellent multi-purpose moisture sealing resin
- Two-part closed mixing pouch simplifies mixing and pouring
- Bonds to itself and to most modern cable jackets
- Thermal setting; designed to not melt or run once cured
- Designed to be stable at elevated temperatures
- Generates its own heat to cure
- Tough & Oil resistant
- RoHS compliant 2002/95/EU*

Applications

- Replace or repair the jacket on both single and multi-core power cables
- Insulate between conductors of multi-core splices operating up to 8,000 volts
- Seal the crotch or sheath when terminating multi-core cables.

Note: This data is not to be used for specifications.

Values listed are typical and should not be considered minimum or maximum.

Typical Properties

		ASTM Standard	
Physical	Color	Black	
	Density	0.65 oz/cu in (1,13 g/cc)	D792
	Hardness	80 Shore D	D2240
	Tensile Strength	4900 psi (33.8 MPa)	D412
	Elongation	4%	D412
	Glass Transition Temperature	118°F (48°C)	E1356-03
	Maximum Exotherm (100g)	338°F (170°C)	D2471-99
	Gel Time @ 73°F (23°C)	16 minutes	D2471-99
	Moisture Absorption @ 73°F	2.6% wt. gain in 168 hrs	
Electrical	Dielectric Strength	500 v/mil	D149
	Dielectric Constant @ 60 Hz		D150
	73°F (23°C)	3.1	
	140°F (60°C)	3.9	
	194°F (90°C)	6.0	
	Dissipation Factor @ 60 Hz		D150
73°F (23°C)	0.5%		
140°F (60°C)	5.1%		
194°F (90°C)	>20%		
Specifications - Product	The material must be supplied in a two-part polyethylene bag with a barrier separating an epoxy and hardener. The barrier must be capable of being broken to permit mixing the two parts without opening the bag.		
Specifications - Engineering/Architectural	The material must be 3M™ Scotchcast™ Electrical Insulating Resin 4. It must be packaged in the 3M two-part, closed mixing pouch. The resin must be mixed within the mixing pouch simply by separating the barrier between the two parts of the bag and working the contents back and forth within the bag.		

⚠ Caution

If there is any evidence of moisture in the cable, it must be removed and the substrate dried before applying the resin.

Installation Techniques

Thoroughly clean and dry the surface of the substrate, to which the resin will be bonded. In the case of synthetic cable jackets, the resin must be poured immediately after the surface is prepared to help create a bond.

Remove the closed mixing bag by tearing the protective envelope.

Premix the darker side of the resin to a smooth consistency, by squeezing, before breaking the barrier. Firmly grasp each flat side of the bag near the center barrier, while pulling the sides of the barrier apart and rolling the sides of thumbs through the barrier. Break the barrier all the way across to the side seals.

Alternately squeeze each end of the bag forcing the resin back and forth. Strip the resin from the corners of the bag. Mix until the color is uniform (30 to 40 squeezes). Approximately one to two minutes.

Clip off a corner of the closed mixing pouch and pour into the mold fill spout, maintaining a half-inch head. For the 4D-NZ delivery, break the second seal and pour through the nozzle.

Typical Cure Times:

<u>Temp</u>	<u>Cure Time</u>
70°F (21°C)	1 to 2 hours
50°F (10°C)	4 to 8 hours

NOTE: 3M™ Scotchcast™ Electrical Insulating Resin 4 is not impaired by freezing; however, it should be warmed to at least 60°F (16°C) before being mixed or poured.

⚠ Danger

Causes burns. May cause allergic skin reaction. Inhalation of vapors may cause respiratory tract irritation and central nervous system depression.

Contains a chemical(s) which can cause cancer and birth defects or other reproductive harm.

Precautions

Do not get in eyes, on skin, or on clothing. Wear suitable protective clothing, gloves, and eye and face protection. Do not ingest. When using, do not eat, drink or smoke. Avoid breathing vapors. Use only in well ventilated areas. Wash thoroughly after handling. For industrial or professional use only.

First Aid Information

Eye Contact: Immediately flush eyes with large amounts of water for at least 15 minutes. Get immediate medical attention. **Skin Contact:** Remove contaminated clothing and shoes. Immediately flush skin with large amounts of water for at least 15 minutes. Get immediate medical attention. Wash contaminated clothing and clean shoes before reuse. **Inhalation:** Remove person to fresh air. If signs/symptoms develop, get medical attention. **If Swallowed:** Do not induce vomiting. Give person two glasses of water. Never give anything by mouth to an unconscious person. Get immediate medical attention.

Refer to Material Safety Data sheet for additional precautionary information.

Shelf-Life & Storage

3M™ Scotchcast™ Electrical Insulating Resin 4 is stable for a period of two years from date of manufacture when stored at 50-80°F (10-27°C) and below 75% relative humidity.

Notes:

1. If the guard bag is removed, the shelf life could be reduced to as little as two hours under conditions of high humidity.
 2. The appearance of crystals in the liquid resin will not affect product performance.
-

Availability

3M Scotchcast Resin 4 is available from your electrical distributor. Check 3M.com/electrical “Where to Buy” for names and locations.

RoHS Definition

*“RoHS Compliant 2002/95/EC” means that the product or part (“Product”) does not contain any of the substances in excess of the maximum concentration values in EU Directive 2002/95/EC, as amended by Commission Decision 2002/618/EC, unless the substance is in an application that is exempt under RoHS. This information represents 3M’s knowledge and belief, which may be based in whole or in part on information provided by third party suppliers to 3M.

Important Notice:

All statements, technical information, and recommendations related to 3M’s products are based on information believed to be reliable, but the accuracy or completeness is not guaranteed. Before using this product, you must evaluate it and determine if it is suitable for your intended application. You assume all risks and liability associated with such use. Any statements related to the product, which are not contained in 3M’s current publications, or any contrary statements contained on your purchase order shall have no force or effect unless expressly agreed upon, in writing, by an authorized officer of 3M.

**Warranty; Limited Remedy;
Limited Liability:**

This product will be free from defects in material and manufacture at the time of purchase. **3M MAKES NO OTHER WARRANTIES INCLUDING, BUT NOT LIMITED TO, ANY IMPLIED WARRANTY OF MERCHANTABILITY OR FITNESS FOR A PARTICULAR PURPOSE.** If this product is defective within the warranty period stated above, your exclusive remedy shall be, at 3M’s option, to replace or repair the 3M product or refund the purchase price of the 3M product. **Except where prohibited by law, 3M will not be liable for any indirect, special, incidental or consequential loss or damage arising from this 3M product, regardless of the legal theory asserted.**

3M and Scotchcast are trademarks of 3M Company.

**Electrical Markets Division**

6801 River Place Blvd.
Austin, TX 78726-9000
800 245 3573 / 651 737 7222 (24 hours)
www.3M.com/electrical

Please recycle.
© 3M 2008 All rights reserved.
78-8131-7706-6-B